

Technical Note

TN 5.07_C Post Installation Testing for HDPE Pipe

Introduction

HDPE pipe is often tested after or during installation to ensure a sound installation was accomplished. Types of post installation field testing include deflection testing and joint testing. Specific testing required for the project will be found in the project specifications. This technical note is not meant to supersede any project specification, but should be used in conjunction with the project specification and national testing standards as it relates specifically to HDPE pipe.

Deflection Testing

An important feature of any flexible pipe is its ability to deflect, under load without structural distress. Flexible pipe *must* deflect in order to mobilize the strength of the surrounding backfill. Deflection allows the load to be transferred from the pipe to the surrounding backfill. As a result, flexible pipe can withstand very high loads as a relatively light structure.

According to current thermoplastic design procedures, deflection is defined as a service limit. The designer, considering all site conditions, will set this service limit in order to perform a proper design evaluation. Deflection in excess of this service limit does not necessarily result in strength limits being exceeded, i.e. system failure. For more information on service and strength limit states, see the *Structures section* of the Drainage Handbook. HDPE can be expected to perform satisfactorily in most applications with 5% or 7.5% deflection and so it is typical of designers to choose a service limit in this range.

When testing for allowable deflection limits, the minimum inside diameter should be used when establishing mandrel sizing. The minimum inside diameter accounts for the allowable manufacturing tolerances. Table 1 lists the inside diameters that result from 5% and 7.5% deflection from the minimum inside diameter. Values listed in Table 1 should be used for sizing mandrels for deflection testing. Mandrels may be obtained from a variety of commercial suppliers.

Table 1: Base Inside Diameters for HDPE Pipe

Nominal Pipe Diameter mm (in)	Base Inside Diameter mm (in)	Base Inside Diameter with 5% Deflection mm (in)	Base Inside Diameter with 7.5% Deflection mm (in)
100 (4)	97.0 (3.88)	92.0 (3.68)	89.75 (3.59)
150 (6)	145.5 (5.82)	138.25 (5.53)	134.5 (5.38)
200 (8)	194.0 (7.76)	184.25 (7.37)	179.25 (7.17)
250 (10)	242.2 (9.69)	230.25 (9.21)	224.25 (8.97)
300 (12)	290.75 (11.63)	276.25 (11.05)	269.0 (10.76)
375 (15)	363.5 (14.54)	345.5 (13.82)	336.25 (13.45)
450 (18)	436.25 (17.45)	414.5 (16.58)	403.5 (16.14)
600 (24)	581.75 (23.27)	552.5 (22.10)	521.52 (21.52)
750 (30)	727.0 (29.08)	690.75 (27.63)	672.5 (26.90)
900 (36)	872.5 (34.90)	829.0 (33.16)	807.0 (32.28)
1050 (42)	1018.0 (40.72)	967.0 (38.68)	941.5 (37.66)
1200 (48)	1164.0 (46.54)	1105.25 (44.21)	1076.3 (43.05)
1350 (54)	1308.75 (52.35)	1243.25 (49.73)	1210.75 (48.43)
1500 (60)	1492.5 (58.17)	1381.5 (55.26)	1345.25 (53.81)

*Value is per AASHTO M252¹ (100 mm - 250 mm [4"-10"] dia.) and AASHTO M294² (300 mm - 1500 mm [12"-60"] dia.). If designing to a specific standard, please review allowable minimum diameter.

It is important to understand that mandrel testing is a go/no-go test. If any line were to not pass a mandrel, it is important to determine the cause. Obstructions in the line, not associated with deflection, may influence the test. Visual inspection is recommended in the event of a no-go result.

Joint Testing

Joint testing is an important part of any gravity sewer system, both in testing for infiltration and exfiltration. Infiltration aids to estimate the amount of sewer water that will be conveyed to, and ultimately treated by, the waste water treatment plant. Exfiltration aids to estimate the loss of sewage water into the surrounding soil. The two primary ways of testing sewer pipe joints for infiltration and/or exfiltration is using air or water to create a constant pressure within the system. Testing shall be carried in our conformance with clause 8.4, leakage test of CSA B182.11.

Exfiltration Testing with Air

Air is a compressible gas and so it is extremely important one adheres to the appropriate safety regulations and project specifications. There are two primary testing standards that may be applied to joint testing HDPE: ASTM F1417 *Standard Test Method for Installation Acceptance of Plastic Gravity Sewer Lines Using Low-Pressure Air*, and ASTM F3058 *Preliminary Field Testing of Thermoplastic Pipe Joints for Gravity Flow (Non-Pressure) Sewer Lines*. When either standard is specified by the project plans, one should review the standards carefully and follow the testing procedure and safety precautions outlined. The below commentary on the ASTM testing procedures should be considered a summary and does not replace the testing procedures outlined in their respective specifications.

ASTM F1417 entails testing a run of pipe from one manhole to the next adjacent manhole. Inflatable plugs are positioned into the manholes and secured. Air is introduced into the pipe line and gradually builds pressure. Once the line has been pressurized and is stable at 28 kPa (4.0 psi), the pressure is decreased to 24 kPa (3.5 psi) at which time the line must not lose more than 3.5 kPa or 7.0 kPa (0.5 or 1.0 psi) (whichever is specified by the design engineer) in the specified amount of time. Table 2 below summarizes the minimum time that must be reached for less than 3.5 kPa or 7.0 kPa (0.5 or 1.0 psi) of pressure drop, depending on the diameter and length of pipe being tested.

Table 2: Time to Pressure Drop for HDPE (per ASTM F1417)

Pipe Diameter mm (in)	Pressure Drop kPa (psi)	Minimum Test Time (min:s)	Length for Minimum Time, (m [ft])	Time for Longer Lengths, (s)	Time for Length (L), (s)							
					30 m (100 ft)	45 m (150 ft)	60 m (200 ft)	76 m (250 ft)	91 m (300 ft)	106 m (350 ft)	121 m (400 ft)	137 m (450 ft)
300 (12)	3.5 (0.5)	5:40	60 (199)	1.709 L	5:40	5:40	5:42	7:08	8:33	9:58	11:24	12:50
	7.0 (1.0)	11:20		3.418 L	11:20	11:20	11:24	14:15	17:05	19:56	22:47	25:38
375 (15)	3.5 (0.5)	7:05	48 (159)	2.671 L	7:05	7:05	8:54	11:08	13:21	15:35	17:48	20:02
	7.0 (1.0)	14:10		5.342 L	14:10	14:10	17:48	22:15	26:42	31:09	35:36	40:04
450 (18)	3.5 (0.5)	8:30	40 (133)	3.846 L	8:30	9:37	12:49	16:01	19:14	22:26	25:38	28:51
	7.0 (1.0)	17:00		7.692 L	17:00	19:13	25:38	32:03	38:27	44:52	51:16	57:41
600 (24)	3.5 (0.5)	11:20	30 (99)	6.837 L	11:24	17:57	22:48	28:30	34:11	39:53	45:35	51:17
	7.0 (1.0)	22:40		13.764 L	22:47	34:11	43:34	56:58	68:22	79:46	91:10	102:33
750 (30)	3.5 (0.5)	14:10	24 (80)	10.683 L	17:48	26:43	35:37	44:31	53:25	62:19	71:13	80:07
	7.0 (1.0)	28:20		21.366 L	35:37	53:25	71:13	89:02	106:50	124:38	142:26	160:15

Data taken from ASTM F 1417³ and Uni-Bell, Uni-B-6-98⁵. It may not be necessary to hold the test for the entire time period listed above when it is evident that the rate of air loss is zero or less than the allowable pressure drop and authorized by the approving authority¹.

When the pipe is large enough to be physically accessed, it may be desirable to test individual joints for safety reasons. In these cases, one may consider joint testing in accordance with ASTM F3058, also known as a joint isolation test. ADS recommends a joint isolation test, in lieu of a full line test, for testing pipe diameters 900 mm (36") and larger for safety reasons. This test is typically done with air, though water may also be used, and involves the use of special testing equipment. The equipment consists of two inflatable bladders, placed on each side of the joint, creating an open center cavity between them. The bladders are inflated and then the center cavity is pressurized to 24 kPa (3.5 psi). The joint passes the test if the pressure is held for 5 seconds without dropping more than 7.0 kPa (1.0 psi). For all practical purposes, this is a go/no-go test. Final acceptance of the pipeline per this testing method shall be at the discretion of the Design Engineer. One advantage of this type of test is the ability for the installer to quickly test the joint immediately after installation, allowing for any corrective measures to be taken early on in the project.

Infiltration/Exfiltration with Water

Testing gravity sewer joints via water infiltration or exfiltration is a common practice. For HDPE, this testing should be conducted in accordance with ASTM F2487 *Standard Practice for Infiltration and Exfiltration Acceptance Testing of Installed Corrugated High Density Polyethylene Pipelines*. This standard entail first observing the ground water conditions and, if applicable, measuring the infiltration rate of the ground water through the joints. If ground water is not applicable, then the line is filled with water and the leakage is observed through exfiltration.

Manholes shall be tested separately and independently of the pipe line to the requirements established in the project specifications. When water level is measured in the manhole for the exfiltration test, the leakage associated with the manhole shall be subtracted from the overall leakage of the test section to establish a pass or fail grade for the pipe.

Allowable Leakage

The allowable leakage rate for HDPE is 18.5 L/mm-diam./km of sewer/day (200 gallons/in-dia/mi-pipe/day) for both infiltration and exfiltration when tested in accordance with ASTM F2487.

Conclusion

HDPE pipe is intended for gravity flow drainage applications and may be tested for deflection and joint tightness as discussed in this technical document. It is important to note that the testing procedures are no different than for other gravity flow drainage products currently being used in the market. This document does not purport to address the safety concerns associated with testing HDPE pipe. Any questions associated with testing HDPE pipe can be directed to your local representative.

References

1. AASHTO M 252, *Standard Specification for Corrugated Polyethylene Pipe Drainage Pipe*, AASHTO, 2023
2. AASHTO M 294, *Standard Specification for Corrugated Polyethylene Pipe, 300 to 1500 mm (12 to 60 in.) Diameter*, AASHTO, 2021
3. ASTM F1417, *Standard Test Method for Installation Acceptance of Plastic Gravity Sewer Lines Using Low-Pressure Air*, ASTM, 2011 (2024)
4. ASTM F3058, *Preliminary Field Testing of Thermoplastic Pipe Joints for Gravity Flow (non-Pressure) Sewer Lines*, ASTM, 2016. (2021)
5. ASTM F2487, *Standard Practice for Infiltration and Exfiltration Acceptance Testing of Installed Corrugated High Density Polyethylene Pipelines*, ASTM, 2021
6. UNI-B-6-98, *Recommended Practice for Low-Pressure Air Testing of Installed Sewer Pipe*, Uni-Bell PVC Pipe Association, 1998

