



Erosion Protection



Filtration



Separation

## ADS 2403W WOVEN GEOTEXTILE SPECIFICATION

### Scope

This specification describes ADS 2403W woven geotextile.

### Filter Fabric Requirements

ADS 2403W is manufactured using high-tenacity monofilament polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. ADS 2403W resists ultraviolet deterioration, rotting and biological degradation and is inert to commonly encountered soil chemicals. ADS 2403W conforms to the physical property values listed below:

### Filter Fabric Properties

Property	Test Method	Unit	M.A.R.V. (Minimum Average Roll Value) <sup>2</sup>
Tensile Strength (Grab)	ASTM D4632	lbs (N)	425 x 350 (1891 x 1558)
Elongation	ASTM D4632	%	15
CBR Puncture	ASTM D4833	lbs (N)	1340 (59,639)
Trapezoidal Tear	ASTM D4533	lbs (N)	125 x 145 (556 x 645)
UV Resistance (at 500 hours)	ASTM D4355	%	90
Apparent Opening Size (AOS)*	ASTM D4751	U.S. Std. Sieve (mm)	40 (.425)
Percent Open Area (POA)	COE 02215	%	6
Permittivity	ASTM D4491	sec <sup>-1</sup>	.96
Water Flow Rate	ASTM D4491	gpm/ft <sup>2</sup> (lpm/m <sup>2</sup> )	70 (2852)

\* Maximum average roll value.