



Separation

ADS 200W WOVEN GEOTEXTILE SPECIFICATION

Scope

This specification describes ADS 200W woven geotextile.

Filter Fabric Requirements

ADS 200W woven geotextile is manufactured using high-tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. ADS 200W resists ultraviolet deterioration, rotting and biological degradation and is inert to commonly encountered soil chemicals. ADS 200W conforms to the physical property values listed below:

Filter Fabric Properties

Property	Test Method	Unit	M.A.R.V. (Minimum Average Roll Value) ²
Tensile Strength (Grab)	ASTM D4632	lbs (N)	200 (890)
Elongation	ASTM D4632	%	15
CBR Puncture	ASTM D6241	lbs (N)	700 (3115)
Puncture	ASTM D4833	lbs (N)	90 (400)
Mullen Burst	ASTM D3786	psi (kPa)	400 (2756)
Trapezoidal Tear	ASTM D4533	lbs (N)	75 (330)
UV Resistance (at 500 hours)	ASTM D4355	%	70
Apparent Opening Size (AOS)*	ASTM D4751	U.S. Sieve (mm)	40 (.425)
Permittivity	ASTM D4491	sec ⁻¹	.05
Water Flow Rate	ASTM D4491	gpm/ft ² (l/min/m ²)	5 (204)

* Maximum average roll value.

Packaging

Roll Dimensions (W x L) - ft. (m)	12.5 x 432/ 15 x 360 / 17.5 x 309 (3.81 x 131.7/ 4.57 x 109.8 / 5.33 x 94.2)
-----------------------------------	--