



Reinforcement

ADS BX1515 BIAXIAL GEOGRID SPECIFICATION

Product Type:	Integrally Formed Biaxial Geogrid
Polymer:	Polypropylene
Load Transfer Mechanism:	Positive Mechanical Interlock
Primary Applications:	Base Reinforcement, Subgrade Improvement

Product Properties

Index Properties	Unit	MD Values ¹	XMD Values ¹
Aperture Dimensions ²	in (mm)	1.5 (38)	1.5 (38)
Rib Thickness ²	in (mm)	0.035 (0.9)	0.025 (0.6)
Tensile Strength @ 2% Strain ³	lb/ft (kN/m)	340 (5.0)	340 (5.0)
Tensile Strength @ 5% Strain ³	lb/ft (kN/m)	750 (11.0)	750 (11.0)
Ultimate Tensile Strength ³	lb/ft (kN/m)	1030 (15.0)	1030 (15.0)

Structural Integrity

Index Properties	Unit	MD Values ¹	XMD Values ¹
Junction Efficiency ³	%	93	93
Flexural Stiffness ⁵	mg-cm	325,000	325,000
Aperture Stability ⁶	m-N/deg	0.38	0.38

Durability

Index Properties	Unit	MD Values ¹	XMD Values ¹
Resistance to Installation Damage ⁷	%SC / %SW / %GP	95 / 93 / 90	95 / 93 / 90
Resistance to Long Term Degradation ⁸	%	100	100
Resistance to UV Degradation ⁹	%	100	100

Dimensions and Delivery

The biaxial geogrid shall be delivered to the jobsite in roll form with each roll individually identified and nominally measuring 12.5' (3.8 m) in width and 328' (100 m) in length. A typical truckload quantity is 224 rolls.

Notes:

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
2. Nominal dimensions.
3. Determined in accordance with ASTM D6637-10 Method A.
4. Load transfer capability determined in accordance with ASTM D7737-11.
5. Resistance to bending force determined in accordance with ASTM D7748/D7748M-14.
6. Resistance to in-plane rotational movement in accordance with ASTM D7864/D7864M-15.
7. Resistance to loss of load capacity or structural integrity when subjected to mechanical installation stress in clayey sand (SC), well graded sand (SW), and crushed stone classified as poorly graded gravel (GP). The geogrid shall be sampled in accordance with ASTM D5818 and load capacity shall be determined in accordance with ASTM D6637.
8. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
9. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.