



## ADS 370HP WOVEN GEOTEXTILE SPECIFICATION

### Scope

This specification describes ADS 370HP woven geotextile.

### Scope

ADS 370HP woven geotextile is manufactured using high-tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. ADS 370HP resists ultraviolet deterioration, rotting and biological degradation and is inert to commonly encountered soil chemicals. ADS 370HP conforms to the physical property values listed below:

### Filter Fabric Properties

Property <sup>1</sup>	Test Method	Unit	M.A.R.V. (Minimum Average Roll Value) <sup>2</sup>
Wide Width Tensile	ASTM D4595	lbs/ft (kN/m)	3600 x 3300 (52.5 x 48.2)
Wide Width Tensile (2% Strain)	ASTM D4595	lbs/ft (kN/m)	540 x 540 (7.9 x 7.9)
Wide Width Tensile (5% Strain)	ASTM D4595	lbs/ft (kN/m)	1500 x 1560 (21.9 x 22.8)
Wide Width Tensile (10% Strain)	ASTM D4595	lbs/ft (kN/m)	2400 x 2400 (35 x 35)
UV Resistance (at 500 hours)	ASTM D4355	%	80
Apparent Opening Size (AOS)*	ASTM D4751	U.S. Std. Sieve (mm)	30 (0.6)
Permittivity	ASTM D4491	sec <sup>-1</sup>	.52
Permeability	ASTM D4491	cm/sec	.05
Water Flow Rate	ASTM D4491	gpm/ft <sup>2</sup> (l/min/m <sup>2</sup> )	40 (1630)

\* Maximum average roll value

### Packaging

Roll Dimensions (W x L) - ft. (m)	15 x 300 (4.6 x 91.5)
Roll Square Yards (Square Meters)	500 (418)